


QUARTZ

MOTIV COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" loop pile Tufté 1/10" loop pile Getuftet 1/10" loop pile Getuft 1/10" loop pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PP	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Bitumen back Min. 70% recycled content	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 C _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 550 gr/m ²	SIZE DIMENSION ABMESSUNG AFMETING	50 X 50 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 4.300 gr/m ²	PACKAGING EMBALLAGE VERPACKUNG VERPAKKING	5 m ² /b 20 b/p
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 4,0 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 7,0 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 212.760/m ²		
PRODIS / GUT	E306FDDE		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC2		

01/23 All rights reserved to alter technical specification
Sous réserve de modifications techniques
Unter Vorbehalt von technischen Änderungen
Onder voorbehoud van wijzingen van de technische specificaties.



EN 14041
CE
22
ITC CO BV Kanegemstraat 15 - BE 8700 Tielt
DOP: 1010#BIOACL
Textile Floor Covering EN 1307 Notified body 0493
    